## Deep Cycle SLA Battery

#### **DC SERIES**

bosfa

DC (Deep cycle) Series batteries are designed for deep discharge application, with special chemical formula for plates active paste material, slightly stronger electrolyte and low temperature design, which can withstand repeated deep cyclic application, such as Solar Energy System, Golf Trolley, Electric

**VRLA Battery** 

#### **Application**

- Solar Energy System
- Golf Cars and Buggies
- Electric Powered Vehicles
- Wheel Chairs

- Power Tools
- Electric Powered Toys
- Control System
- Vacuum Cleaners
- Medical Equipments

#### **General Features**


- Sealed and maintenance free operation.
- Non-Spillable construction design.
- ABS containers and covers(UL94HB, UL94V-0) optional.
- Safety valve installation for explosion proof.
- High quality and high reliability.
- Exceptional deep discharge recovery performance.
- Low self discharge characteristic.
- Flexibility design for multiple install positions.

#### **Construction**


• ComponentRa	w material
• PositiveLea	ad dioxide
• NegativeLea	ad
• ContainerAB	S
• Cover AR	ς


- Sealant ......Epoxy Resin
- Safety valve ....EPDR
- Terminal ......Copper
- Separator ......Fibre glass • Electrolyte .....Sulfuric acid






**Terminal Dimensions** 








Battery Model	DC 12-60					
Designed Cycle Life	> 350 cycles @ -0.5CA to 9.6V					
Capacity(25°C)	20HR(3.1A,1.75V) 10HR(6.0A,1.75V) 5HR(10.2A,1.75V)		5HR(10.2A,1.75V)	1HR(39A,1.75V)		
	62AH	62AH 60AH 51AH		39AH		
Dimensions	Length	Width	Height	Total Height		
	260mm(10.24inch)	170mm(6.69inch)	221mm(8.70inch)	221mm(8.70inch)		
Approx. Weight	21Kg (46.31 lbs)					
Internal Resistance	Full charged at 25°C: 0.0075 Ohm					
Self Discharge	3% of capacity declined per month at (25°C)					
Capacity Affected by Temp.(20HR)	acity Affected 40°C		0°C	-15°C		
	102%	100%		65%		
Charge Voltage(25°C)	Cycle	e use	Float use			
	14.4-15V(-30mV/ °C)	), max. Current: 15A	13.6-13.8V(-20mV/ °C)			

**VRLA Battery** 

# Deep Cycle SLA Battery



#### Constant current discharge ratings-amperes at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	210	144	105	63.0	39.6	16.4	11.4	6.36	3.16
1.67V	189	131	102	61.2	39.5	16.3	11.4	6.27	3.15
1.70V	179	127	98.4	60.0	39.4	16.3	11.4	6.22	3.15
1.75V	160	117	93.0	58.8	39.0	16.2	11.3	6.11	3.14
1.80V	144	109	88.8	57.0	38.5	16.1	11.2	6.01	3.03
1.85V	109	89.4	76.8	52.4	38.1	16.1	11.1	5.90	2.84

### Constant power discharge ratings-watts at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	346	239	186	119	78.0	31.4	21.9	12.7	6.3
1.67V	328	236	184	116	75.4	31.4	21.9	12.5	6.3
1.70V	307	230	181	113	73.4	31.4	21.9	12.4	6.3
1.75V	286	215	170	110	72.8	31.0	21.7	12.2	6.3
1.80V	256	200	160	107	71.5	30.5	21.3	12.0	6.1
1.85V	205	166	140	98.4	70.9	30.4	21.0	11.8	5.7







COPYRIGHT BOSFA INDUSTRIAL BATTERY CO.,LTD.